

Zinc Dust Grounding GZ-70

Special paint on zinc dust base with 99.9 % pure zinc, without diluent and without other pigment portions.

Made on epoxy ester base. Corresponds in its composition to Material No. 588.20.38 of Deutsche Bundesbahn (German Federal Railway).

Primer for highly strained objects as e.g. steel structures, ship bodies, industrial plants and automobile parts.

Requires in any case metallic bare, sand-blasted ground (substrate). Suitable for spot welding. After drying can be varnished over with all one-component varnishes. More than 90 % zinc in dry-film.

Delivery units:	0.5 kg 1.0 kg 2.0 kg 6.0 kg 12.0 kg 24.0 kg
Delivery form:	liquid, paintable
Consumption:	300 – 500 g per square meter
Ground (substrate):	sand blasting Sa 2 ½
Drying mode:	air drying
Dust dry:	after approx. 30 min.
Drying time:	dried through over night
Layer thickness:	per coat at least 40 – 50 µm
Coating:	proposition on steel: 1 – 2 x primer 1 – 2 x surface varnish
Application:	brushing, spraying, rolling, suitable for airless
Processing instruction:	stir well before applying!
Use:	exterior and interior
Suitable for varnishing over:	with all 1C-varnishes
Thinner:	special thinner VK-80
Density:	approx. 2.6 kg/l
Tone of colour:	grey
Safety and danger identification:	see safety data sheet

TM/GZ-70 revised: 25th April 2005 / printout: 16.08.06/GB