

Industrial Gloss Paint

LK-52

Quick-drying corrosion protection and metal protection coating with very high solid content.
Glossy.

Suitable for new coatings, maintenance and repair coatings on machines and devices, parts of buildings, receptacles and containers.

Versatile application range, also without prior priming coat. Single-coat paint.

Containers:	Buckets with 1.0 litre Buckets with 2.5 litres Buckets with 5.0 litres Buckets with 12 kg Hobbocks with 30 kg
Order no.	e.g.: LK-52.00.9016.1, colour shade: traffic white
Delivery form:	Ready to use
Colour shades:	According to RAL and other specifications
Drying method:	Air drying
Drying time:	Approx. 2 – 3 hours depending on temperature
Dust dry:	After approx. 30 minutes
Spreading rate:	Approx. 5 – 6 m ² /kg
Density:	Approx. 1.05 g/ml depending on colour shade
VOC/EU limit value:	Cat. A/i: 600g/l (2007), 500 g/l (2010). This product contains 600 g/l VOC max.
Application:	By brush, spray, roller
Film thickness:	Approx. 40 µm per coat
Solvent:	VK-30
Added thinner:	The spray parameters must be selected such that thinning of the product is not necessary.
Storage stability:	At least 1 year
Sheen level:	Glossy, 80 on average and above depending on colour shade
Flash point:	Above +23°C
Delivered viscosity:	Above 60 sec. ALZ/DIN 4 mm
VbF¹:	Not applicable
GGVS(ADR)/GGVE(RID):	Not applicable
Application range:	Inside and outside
Instructions for use:	Stir well before use
Substrates:	Substrates must be free from dirt, rust, oil, grease, brittle paints, moisture
Coating recommendation:	1 – 2 coats, with and without primer, depending on stress
Safety and hazard labelling:	See Safety Data Sheet

¹ Regulations on inflammable liquids

TM/LK-52 revised: 16.10.08 rei/in / printout: 16.10.08/GB