

## Thick-film zinc repair compound

### LZ-09

Zinc metal thick-film coating system for repairing flaws in hot-dip galvanised steel parts, as well as for galvanised surfaces damaged during grinding or welding, and for non-galvanised small steel parts that are to be matched to galvanised constructions.  
**Conforms to the requirements of standard DIN EN ISO 1461.**

<b>Supply sizes:</b>	100 ml 250 ml 500 ml 1.0 l 2.5 l 5.0 l 12,0 kg
<b>Supply form:</b>	high-viscosity, ready to use
<b>Drying method:</b>	air drying
<b>Drying time:</b>	over night
<b>Dust dry:</b>	after approx. 1 hour
<b>Over-paintable:</b>	yes, e.g. with Zinc Coat LZ-80
<b>Consumption:</b>	approx. 8 m <sup>2</sup> /l
<b>Application:</b>	predominantly by brushing and rolling
<b>Substrate:</b>	clean thoroughly before applying; thoroughly remove loose matter such as rust, white rust, scale, soot, grease and other impurities
<b>Solvents:</b>	VE-50, VK-30 or VK-80
<b>Coat thickness:</b>	100 µm per coat (dry)
<b>Shelf life:</b>	min. 1 year
<b>Density:</b>	approx. 1.2 kg/l
<b>VOC – EU limit value:</b>	Cat. A/i: 500 g/l (2010). This product contains max. 500 g/l VOC.
<b>Application:</b>	outdoor and indoor
<b>Gloss level:</b>	silk matt
<b>Colour:</b>	available in 6 different shades from light to dark, see our colour card no. 6
<b>Safety and risk designation:</b>	see safety data sheet

TM/LZ-09 überarbeitet am: 24.02.10 rei/mh / Druckdatum: 24.02.10/01-03/GB